

Solder Bar

Model: H63S-B

Rev.2012/12/03 Ver.06-00

— Specification —

Item	Specification
Alloy Composition	Sn/Pb37
Appearance	Bright and shiny surface finishes.
Shape	Bar.
Density	Approx. 8.4 g/cm ³ (20 °C)
Melting Point	Approx. 183°C.
Packaging	Net weight Approx. 20kg/carton.
Feature	Produced by pure tin and lead. Impurities are low to the minimum.
Application	For wave soldering process.
Reference Standard	JIS-Z-3282
Storage and Handling	Storage must be in a dry, non-corrosive and shine environment.
Shelf life	Shelf life is 2 years from date of manufacture.

— Alloy Composition —

Sn	Pb	Sb	Bi	Cd	Cu	Au	In	Ag	Al	As	Fe	Ni	Zn
62.5~63.5	REM.	0.05 Max	0.05 Max	0.002 Max	0.08 Max	0.05 Max	0.10 Max	0.10 Max	0.001 Max	0.03 Max	0.02 Max	0.01 Max	0.001 Max

(wt %)

Contact Information

SHENMAO TECHNOLOGY INC.

Add: No.12-1 Gongye 2nd Rd., Guanyin industrial area, Taoyuan County 328, Taiwan.

Tel: (886)3-416-0177

Fax: (886)3-416-0133

Mail: sales@shenmao.com

BRANCHES:

Please refer to our website.

Website: <http://www.shenmao.com>